

IMPERFECTION OF COMPOSITE LAMINATED PLATES

Osama Mohammed Elmardi Suleiman

Department of Mechanical Engineering, Faculty of Engineering and Technology, Nile Valley University, Atbara

Sudan

ABSTRACT

It is found that the manufacturing processes are responsible of many defects which may arise in fibers, matrix and lamina. These defects, if they exist include misalignment of fibers, cracks in matrix, non – uniform distribution of the fibers in the matrix, voids in fibers and matrix, delaminated regions, and initial stress in the lamina as a result of its manufacture and further treatment.

The above mentioned defects tend to propagate as the lamina is loaded causing an accelerated rate of failure. The experimental and theoretical results in this case tend to differ. Hence, due to the limitations necessary in the idealization of the lamina components, the properties estimated should be proved experimentally.

Keywords: Composite laminates, imperfections, delamination, fiber, matrix.

1. INTRODUCTION

It is important to recognize that, with the advent of composite media, certain new material imperfections can be found in composite structures in addition to the better – known imperfections that one finds in metallic structures. Thus, broken fibers, delaminated regions, cracks in the matrix material, as well as holes, foreign inclusions and small voids constitute material and structural imperfections that can exist in composite structures. Imperfections have always existed and their effect on the structural response of a system has been very significant in many cases. These imperfections can be classified into two broad categories: initial geometrical imperfections and material or constructional imperfections.

The first category includes geometrical imperfections in the structural configuration (such as a local out of roundness of a circular cylindrical shell, which makes the cylindrical shell non – circular; a small initial curvature in a flat plate or rod, which makes the structure non – flat, etc.), as well as imperfections in the loading mechanisms (such as load eccentricities; an axially loaded column is loaded at one end in such a manner that a bending moment exists at that end). The effect of these imperfections on the response of structural systems has been investigated by many researchers and the result of these efforts can be easily found in published papers [1-18].

The second class of imperfections is equally important, but has not received as much attentions as the first class; especially as far as its effect on the buckling response characteristics is concerned. For metallic materials, one can find several studies which deal with the effect of material

Osama Mohammed Elmardi Suleiman, Imperfection of composite laminated plates

imperfections on the fatigue life of the structural component. Moreover, there exist a number of investigations that deal with the effect of cut – outs and holes on the stress and deformation response of thin plates. Another material imperfection is the rigid inclusion. The effect of rigid inclusions on the stress field of the medium in the neighborhood of the inclusion has received limited attention. The interested reader is referred to the bibliography of Professor Naruoka[1].

There exists two important classes of material and constructional – type imperfections, which are very important in the safe design, especially of aircraft and spacecraft. These classes consist of fatigue cracks or cracks in general and delamination in systems that employ laminates (fiber – reinforced composites). There is considerable work in the area of stress concentration at crack tips and crack propagation. Very few investigations are cited, herein, for the sake of brevity. These include primarily those dealing with plates and shells and non – isotropic construction. Some deal with cracks in metallic plates and shells [19-22]. Others deal with non – isotropic construction and investigate the effects of non – isotropy [23 – 28]. In all of these studies, there is no mention of the effect of the crack presence on the overall stability or instability of the system.

2. DELAMINATION OF COMPOSITE STRUCTURES

Delaminations are one of the most commonly found defects in laminated structural components. Most of the work found in the literature, deals with flat configurations.. Composite structures often contain delamination. Causes of delamination are many and include tool drops, bird strikes, runway debris hits and manufacturing defects. Moreover, in some cases, especially in the vicinity of holes or close to edges in general, delamination starts because of the development of interlaminar stresses. Several analyses have been reported on the subject of edge delamination and its importance in the design of laminated structures. A few of these works are cited [29–35]. These and their cited references form a good basis for the interested reader. The type of delamination that comprises the basic and primary treatise is the one that is found to be present away from the edges (internal). This delaminating could be present before the laminate is loaded or it could develop after loading because of foreign body (birds, micrometer, and debris) impact. This is an extremely important problem especially for laminated structures that are subject to destabilizing loads (loads that can induce instability in the structure and possibly cause growth of the delamination; both of these phenomena contribute to failure of the laminate). The presence of delamination in these situations may cause local buckling and / or trigger global buckling and therefore induce a reduction in the overall load – bearing capacity of the laminated structure. The problem, because of its importance, has received considerable attention.

3. CONCLUSION

In most of the previous studies, the composite media are assumed free of imperfections i.e. initial geometrical imperfections due to initial distortion of the structure, and material and / or constructional imperfections such as broken fibers, delaminated regions, cracks in the matrix material, foreign inclusions and small voids which are due to inconvenient selection of fibers / matrix materials and manufacturing defects. Therefore, the fibers and matrix are assumed perfectly bonded.

International Journal of Engineering Research And Advanced Technology(IJERAT) ISSN: 2454-6135 [Volume. 02 Issue.09, September– 2016]

www.sretechjournal.org

REFERENCES

- [1] Naruoka M., 'Bibliography on theory of plates', Gihodo, Tokyo.
- [2] Winterstetter Th. A. and Schmidt H., 'Stability of circular cylindrical steel shells under combined loading', Thin walled structures; (2002), 40:PP.893 909.
- [3] Pircher M., and Bridge R., 'The influence of circumferential weld induced imperfections on the buckling of silos and tanks', Journal of constructional steel research; (2001), 57 (5): PP.569 –580.
- [4] Deml M., and Wunderlich W.,' Direct evaluation of the worst imperfection shape in shell buckling', Computer methods in applied mechanics and engineering; (1997), 149 [1 4] : PP.201 222
- [5] Arbocz J., and Starnes J.H., Future directions and challenges in shell stability analysis, Thin walled structures; (2002), 40: PP.729-754
- [6] Arbocz J., The effect of imperfect boundary conditions on the collapse behavior of anisotropic shells, International Journal of solids and structures; (2000), 37: PP.6891 –6915
- [7] Huhne C., Zimmermann R., Rolfes R., and Geier B., 'loading imperfections experiments and Computations', Euromech Colloquiu), the Netherlands.
- [8] Geier B., Klein H., and Zimmermann R., Buckling tests with axially Compressed unstiffened cylindrical shells made from CFRP', proceedings, International Colloquium on buckling of shell structures on land, in the sea, and in the air, Elsevier applied sciences; (1991), London and New York: PP.498–507.
- [9] Geier B., Klein H., and Zimmermann, Experiments on buckling of CFRP Cylindrical shells under non uniform axial load, proceedings of international conference on Composites engineering; (1994).
- [10] Albus J., Gomez Garcia J., and Oery H.,' Control of assembly induced stresses and deformations due to the waviness of the interface flanges of the ESC A upper stage', 52nd International astronautical congress; (2001), Toulouse, France.
- [11] Zimmermann R.,' Buckling research for imperfection tolerant fiber composite structures', proceeding of the conference on spacecraft structures, material and mechanical testing, Nordwijk, The Netherlands: (1996).
- [12] Meyer Piening H.R., Farshad M., Geier B., and Zimmermann, 'Buckling loads of CFRP Composite cylinders under combined axial and torsion loading experiments and computations', Composite structures; (2001), 52:PP.427 –435.
- [13] CMH 17 (Composite Material Handbook 7), Material science corporation; (2010).
- [14] Guo S.J., Stress concentration and buckling behavior of shear loaded composite panels with reinforced cutouts, Composite structures; (2007):PP.1–9
- [15] Remmers J.J.C., and de Borst R.,' Delamination buckling of fiber metal laminates', Composite science and technology; (2001):PP.2207 –2213

Osama Mohammed Elmardi Suleiman, Imperfection of composite laminated plates

- [16] Vit Obdrzalek, and Jan Vrbka, Buckling and post buckling of a large delaminated plate subjected to shear loading, Engineering mechanics, vol. 16; (2009), No.4: PP. 297 –312
- [17] Vit Obdrzalek, and Jan Vrbka,' On buckling of a plate with multiple delamination', Engineering mechanics, vol.17; (2010), No. 1:PP.37 –47
- [18] Keiichi Nemoto, Hirakazu Kasuya, Hisao Kikugawa, and Takashi Asaka,' post buckling behavior of composite laminated plates with initial imperfections under biaxial compression', Materials transactions, vol.50,No.2;(2009):PP.299 304.
- [19] Takao Y., Taya M., and Chou T.W.,' Stress field due to cylindrical inclusion with constant axial eingenstrain in an infinite elastic body', Journal of applied mechanics; (1981) 48 (4):PP.853 858.
- [20] Lakshminarayana H.V., and Murthy M.V.V., On stresses around an arbitrarily oriented Crack in cylindrical shell, International Journal of fracture; (1976), 12(4):PP. 547 566.
- [21] Twee J., and Rooke D.P,' The stress intensity factor for a crack at the edge of a loaded hole', International Journal of solids and structures; (1979),15:PP.899–906.
- [22] Dyshel M.S.,' Fracture of plates with cracks under tension after loss of stability', Journal of applied mathematics and mechanics (PMM); (1981),17(4):PP.77 83.
- [23] Erdogan F., Ratwani M., and Yuceoglu U., On the effect of orthotropy in a cracked cylindrical plates', International Journal of fracture; (1974), 10 (4):PP.369 –
- [24] Krenk S.,' Influence of transverse shear on an axial crack in a cylindrical shell', International Journal of fracture; (1978), 14(2): PP. 123 –
- [25] Delale F., and Erdogan F., Effect of transverse shear and material orthotropy in a cracked spherical cap', International Journal of solids and structures; (1979), 15:PP.907 –926
- [26] Lakshminarayana H.V., and Murthy M.V.V,' On a finite element model for the analysis of through cracks in laminated anisotropic cylindrical shells', Engineering fracture mechanics; (1981)(4):PP.697 712.
- [27] Theocaris P.S., and Milios J., Crack arrest at a bimaterial interface, International Journal of solids and structures; (1981), 17:PP.217 230
- [28] Rogers T.G., 'Crack extension and energy release rates in finitely deformed sheet reinforced with inextensible fibers', International Journal of solids and structures; (1982), 18:PP.705 721
- [29] Kachanov L.M., Separation failure of composite materials, polymer mechanics; (1976), 62):PP.812 815.
- [30] Williams J.G., and et al., Recent developments in the design, testing and impact damage tolerance of stiffened composite plates, NASA TM 80077; (1979), April.
- [31] Wilkins D.J, and et al., Characterizing delamination growth in graphite epoxy', Damage in composite materials; (1982): PP. 168 183.
- [32] Wang S.S., Edge delamination in angle ply composite laminates, AIAA Journal; (1984) (2):PP. 256 264.



International Journal of Engineering Research And Advanced Technology(IJERAT) ISSN: 2454-6135 [Volume. 02 Issue.09, September– 2016] www.sretechjournal.org

[33] Scott W. Beckwith,' Manufacturing defects in composite structures', Sample Journal, volume48, No.5; September/October 2012.

[34] M. Vable, 'Stability of columns', Mechanics of materials; (2014): chapter eleven, PP.496 – 528.

[35] CPNI EBP, Influence of delamination of laminated glass on its blast performance, July 2013.

Author



Osama Mohammed Elmardi was born in Atbara, Sudan in 1966. He received his diploma degree in mechanical engineering from Mechanical Engineering College, Atbara, Sudan in 1990. He also received a bachelor degree in mechanical engineering from Sudan University of science and technology – Faculty of engineering in 1998, and a master degree in solid mechanics from Nile valley university (Atbara, Sudan) in 2003. He contributed in teaching some subjects in other universities such as Red Sea University (Port Sudan, Sudan), Kordofan University (Obayed, Sudan), Sudan University of Science and Technology (Khartoum, Sudan) and Blue Nile university (Damazin, Sudan). In addition he supervised more than hundred and fifty under graduate studies in diploma and B.Sc. levels and about fifteen master theses. He is currently an assistant professor in department of mechanical engineering, Faculty of Engineering and Technology, Nile Valley University. His research interest and favourite subjects include structural mechanics, applied mechanics, control engineering and instrumentation, computer aided design, design of mechanical elements, fluid mechanics and dynamics, heat and mass transfer and hydraulic machinery.